



EXODISP

EXOSTRUCT

CONSTRUCTION

EXOSTRUCT XSBR LATICES

EXODISP ACRYLIC (CO)POLYMERS

CEMENT MODIFICATION

Product	Solids (%)	Viscosity (mPas)	pH	MFFT/Tg (°C)	Backbone	Features & Uses
Exostruct 6050	50	<300	8-9	<1/-22	xSBR	good flexibility at low temperature
Exostruct 6061	46	<300	8.5-9.5	<1/-16	xSBR	flexible general purpose cement modifier
Exostruct 6066	48	<300	8.5-9.5	5/5	xSBR	general purpose cement modifier
Exostruct 6090	50	<500	7-8	9/10	xSBR	cement modifier, enhanced workability
Exodisp C 4700	50	<500	8-9	3/1	Acr	high quality acrylic cement modifier
Exodisp C 7301	50	<6000	7-8	14/18	SAE	styrene acrylic cement modifier

DAMP PROOFING

Product	Solids (%)	Viscosity (mPas)	pH	MFFT/Tg (°C)	Backbone	Features & Uses
Exostruct 6231	53	<300	7-8	<1/-8	xSBR	excellent water resistance & damp proofing
Exostruct 6232	51	<300	8-9	<1/-8	xSBR	excellent water resistance & damp proofing, low ammonia
Exostruct 6263	51	<300	7-8	5/5	xSBR	excellent water resistance & damp proofing
Exostruct 6280	51	<300	7-8	35/35	xSBR	excellent water resistance & damp proofing, hard
Exodisp C 7325	50	<450	7-8	<1/-5	SAE	excellent water resistance, elastomeric

CEMENTITIOUS WATER PROOFING

Product	Solids (%)	Viscosity (mPas)	pH	MFFT/Tg (°C)	Backbone	Features & Uses
Exodisp C 7920	56.5	<1000	7-8	<1/-13	SAE	APEO free, low ammonia, drinking water approved, 2K sealing applications

BITUMEN MODIFICATION

Product	Solids (%)	Viscosity (mPas)	pH	MFFT/Tg (°C)	Backbone	Features & Uses
Exostruct 6061	46	<300	8.5-9.5	<1/-16	xSBR	general purpose bitumen modifier
Exostruct 6263	51	<300	7-8	5/5	xSBR	increased water resistance & cohesion
Exostruct 6720	50	<300	7.5-8.5	<1/-38	xSBR	excellent low temperature flexibility
Exodisp C 7305	50	<6000	7-8	<1/-5	SAE	styrene acrylic flexible bitumen modifier
Exodisp C 7920	56.5	<1000	7-8	<1/-5	SAE	styrene acrylic flexible bitumen modifier

CURING CONTROL

Product	Solids (%)	Viscosity (mPas)	pH	MFFT/Tg (°C)	Backbone	Features & Uses
Exodisp B 6000	15	<500	7-9	<10/31	A	ready-to-use, curing agent
Exodisp B 6001	45	<2000	6-8	<10/31	A	curing agent, concentrate



EOC Belgium nv
Emulsion Division

p/a IP De Bruwaan 12
B-9700 Oudenaarde

T +32 55 23 58 58
F +32 55 23 58 59

emulsions@eocgroup.com
www.eocgroup.com

All recommendations for the use of our products, whether given by us in writing, orally, or to be implied from data or test results obtained by us, are based on the current state of our knowledge at the time such recommendations are made. When additional information is obtained, these recommendations may be updated. They may also be influenced by circumstances outside our control. Notwithstanding such recommendations, the user is responsible to determine that the product as supplied by us, is suitable for the process or purpose he intends to use it. The user of the product is solely responsible for compliance with all laws and regulation applying to the use of the product. Since we cannot control the application, use or processing of the products, we do not accept responsibility therefore. The user shall ensure that the intended use of the products will not infringe in any party's intellectual property rights.